

IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Currently Amended): An aqueous dispersion comprising a silicon-aluminium mixed oxide powder, wherein the particles of said silicon-aluminium mixed oxide powder ~~comprises~~ comprise from 0.1 to 99.9 wt.%  $\text{Al}_2\text{O}_3$  and ~~[[has]]~~ possess a structure containing Si-O-Al- bonds and at least one selected from the group consisting of amorphous silicon dioxide regions, crystalline silicon dioxide regions, and combinations of amorphous and crystalline silicon dioxide regions, and crystalline aluminium oxide regions, the aqueous dispersion having been produced by dispersing the silicon-aluminum mixed oxide in an aqueous medium with an energy input of at least 200 KJ/m<sup>2</sup>.

Claim 2 (Currently Amended): The aqueous dispersion according to claim 1, wherein the powder ~~comprises~~ contains primary particles of amorphous silicon dioxide and crystalline aluminium oxide obtained from a flame hydrolysis process.

Claim 3 (Currently Amended): The aqueous dispersion according to claim 1, wherein the silicon-aluminium mixed oxide ~~has a~~ powder contains a mullite structure having the chemical composition  $3 \text{ Al}_2\text{O}_3 \times 2 \text{ SiO}_2$  up to  $2 \text{ Al}_2\text{O}_3 \times \text{SiO}_2$ .

Claim 4 (Currently Amended): The aqueous dispersion according to claim 1[,]  
~~further comprising~~ containing aluminium oxide doped with silicon dioxide or silicon dioxide obtained from a flame hydrolysis process and doped with aluminium oxide.

Claim 5 (Currently Amended): The aqueous dispersion according to claim 1[,]  
~~further comprising~~ containing aluminium oxide powder completely or partially coated with

silicon dioxide or silicon dioxide powder completely or partially coated with aluminium oxide.

Claim 6 (Original): The aqueous dispersion according to claim 1, wherein the crystalline aluminium oxide regions comprise crystalline aluminum oxide selected from the group consisting of alpha aluminium oxide, gamma-aluminium oxide, delta-aluminium oxide, theta-aluminium oxide, kappa-aluminium oxide, pyrogenically produced aluminium oxide and mixtures thereof.

Claim 7 (Original): The aqueous dispersion according to claim 1, wherein the specific surface area of the powder is between 5 and 300 m<sup>2</sup>/g.

Claim 8 (Currently Amended): The aqueous dispersion according to claim 1, wherein [[a]] the solids content in the dispersion is between 0.1 and 70 wt.%.

Claim 9 (Original): The aqueous dispersion according to claim 1, wherein the pH value of the dispersion is between 4 and 12.5.

Claim 10 (Original): The aqueous dispersion according to claim 1, further comprising an oxidising agent selected from the group consisting of hydrogen peroxide, hydrogen peroxide adducts, organic peracids, inorganic peracids, imino peracids, persulfates, perborates, percarbonates, oxidising metal salts and mixtures thereof.

Claim 11 (Original): The aqueous dispersion according to claim 1, further comprising an oxidation activator selected from the group consisting of metal salts of Ag, Co, Cr, Cu, Fe,

Mo, Mn, Ni, Os, Pd, Ru, Sn, Ti, V, carboxylic acids, nitriles, ureas, amides, esters and mixtures thereof.

Claim 12 (Original): The aqueous dispersion according to claim 1, further comprising a corrosion inhibitor selected from the group consisting of benzotriazoles, substituted benzimidazoles, substituted pyrazines, substituted pyrazoles and mixtures thereof.

Claim 13 (Original): The aqueous dispersion according to claim 1, further comprising non-ionic amphoteric surface-active substances, cationic amphoteric surface-active substances, anionic amphoteric surface-active substances, amphoteric surface-active substances and mixtures thereof.

Claim 14 (Currently Amended): A process for producing the aqueous dispersion according to claim 1, said process comprising dispersing the silicon-aluminium mixed oxide in an aqueous medium,

wherein  $[[an]]$  the energy input for the dispersion operation is at least  $200 \text{ KJ/m}^3$ .

Claim 15 (Original): The process for producing the aqueous dispersion according to claim 14, wherein the silicon-aluminum mixed oxide is dispersed and ground by pressurizing and releasing one or more aqueous dispersions of the silicon-aluminum mixed oxide through a nozzle of a device to cause the one or more aqueous dispersions to collide with one another or a section of a wall of the device.

Claim 16 (Original): A process for chemical mechanical polishing a surface, said process comprising

polishing said surface with the aqueous dispersion claimed in claim 1.

Claim 17 (Original): The process as claimed in claim 16, wherein the surface is an oxide surface.

Claim 18 (Original): A process for chemical mechanical polishing a metal coating, said process comprising  
polishing said metal coating with the aqueous dispersion claimed in claim 1.

Claim 19 (Original): The process as claimed in claim 18, wherein the metal coating is selected from the group consisting of aluminum, aluminum alloys, copper, copper alloys, tungsten, titanium and titanium nitride.

Claim 20 (Original): A surface coating comprising the aqueous dispersion claimed in claim 1.

Claim 21 (Original): A process for producing a surface coating, said process comprising  
incorporating the aqueous dispersion claimed in claim 1 in said surface coating.

Claim 22 (New): An aqueous dispersion comprising silicon-aluminum mixed oxide powder according to claim 1 having an average particle size of less than 150 nm.

Claim 23 (New): An aqueous silicon-aluminum mixed oxide powder according to claim 21 having an average particle size of less than 100 nm.